



Rougier Afrique International

Managing forests. Enriching wood.



OKOUGREEN ECO

Okougreen is produced with Okoume face veneers
for humid and less extreme exterior environment



APPLICATIONS:

- Utility
- General joinery
- Construction in humid and exterior environment
- Industrial packaging
- Furniture

GENERAL INFORMATION

Faces	B/BB (II/III) as per EN 635-2 Okoume (Aucoumea klaineana) face; natural full sheet - back; natural full sheet or jointed
Finish	Calibrated and both sides sanded
Glue	Class 3 phenolic EN 314-2 E1/2 EN717-1
Formaldehyde emission	(EN 717-1): < 0.01 mg/m ³ (test conducted on 16 April 2026)
Density	480-500 kg/m ³ (+/- 10%) According EN 323
Dimensional tolerance	according EN 315
Legality	EUTR and EUDR compliant
Marking	CE2+ for structural use ≥ 8 mm according to EN 13986 CE for non-structural use < 8 mm according to EN 13986

2500x1220 mm

Thickness	plies	pcs/crate
8 mm	5-ply	106
10 mm	5-ply	88
12 mm	7-ply	72
15 mm	7-ply	58
18 mm	9-ply	49
19 mm	9-ply	46
22 mm	11-ply	40
25 mm	13 ply	
30 mm	15-ply	
40 mm	17-ply	



The given information in this datasheet is non-binding and can be changed without prior notice.