



Rougier Afrique International

Managing forests. Enriching wood.



OKOUGREEN

Okougreen is produced with 100% Okoume veneers for universal exterior environment

GENERAL INFORMATION

Species	100% Okoume (Aucoumea klaineana)
Faces	B/BB (II/III) as per EN 635-2 (face; natural full sheet, back; natural full sheet or jointed)
Finish	Calibrated and both sides sanded
Glue	Class 3 phenolic EN 314-2 E1/2 EN717-1
Formaldehyde emission	(EN 717-1): < 0.01 mg/m ³ (test conducted on 16 April 2026)
Density	480-500 kg/m ³ (+/- 10%) EN 323
Dimensional tolerance	according EN 315
Technical certification	NF Extérieur CTB-X (FCBA No ID 80)
Sustainability certification	FSC® 100% (certificate FSC® C14362,CU-COC-874178) on demand
Legality	EUTR and EUDR compliant
Marking	CE2+ for structural use ≥ 8 mm according to EN 13986 CE for non-structural use < 8 mm according to EN 13986

APPLICATIONS:

- Construction in humid and exterior environment
- Fittings of vans and commercial vehicles
- Indoor and outdoor furniture
- Industrial packaging



	2500x1220 mm		3100x1530 mm	
Thickness	plies	pcs/crate	plies	pcs/crate
4 mm	3-ply	200	3-ply	168
5 mm	3-ply	160	3-ply	100
6 mm	5-ply	146	5-ply	112
8 mm	5-ply	106	5-ply	81
10 mm	5-ply	88	5-ply	67
12 mm	7-ply	72	7-ply	55
15 mm	7-ply	58	7-ply	45
18 mm	9-ply	49	9-ply	37
19 mm	9-ply	46	9-ply	33
22 mm	11-ply	40	11-ply	30
25 mm	11-ply	35	11-ply	26
30 mm	13-ply	29	13-ply	22
35 mm	15-ply	25	15-ply	19
40 mm	17-ply	22	17-ply	16

The given information in this datasheet is non-binding and can be changed without prior notice.